


A 25-8 TYPE WATERSTOP

- They can be used in low, medium and high expansion joints, shear movements and water pressure of any intensity.
- > The application method is centralized.
- Waterstops can be joined to each other by heat (thermal) welding (150 °C - 180 °C).

TECHNICAL DATA

General Application Areas of Waterstop

- Dams,
- Irrigation canals,
- Water tanks, reservoirs,
- Water purification plants,
- Swimming pools,
- Docks Transmission tunnels,
- Hydroelectric power plants,
- Bridges,
- Metro constructions,
- > Viaducts,
- Retaining walls,
- Slabs on ground and foundations,
- Industrial structures.



Product Code	L	<i>a</i> 1	a2	b	С	d	R	Production Length
A 25-8	250 ± 4	8.0 ± 0.5	10 ± 1	25 ± 2	45 ± 2	25	6	20 meters

Waterstop dimensions are in millimeters.

ARFEN İNŞAAT VE YAPI TEKNOLOJİLERİ SAN. TİC. A.Ş.

Arfen Headquarter: İstanbul / Türkiye T: +90 212 485 16 15 arfen@arfen.com



Mechanical Properties

Analysis		Basic requireme	nt	Unit	Standard
Toncilo stronght (g)	Ave	rage value	At least 14	N/mm²	TS 3078
Tensile strenght (σ_0)	Sma	ıllest value	At least 12	N/mm²	TS 3078
Elongation rate at	Ave	rage value	At least 225	%	TS 3078
break (ε_o)	Smc	ıllest value	At least 200	%	TS 3078
Type A Shore durometer	hardness rating	(H _o)	75 ± 5	Shore A	TS 3078
Unit volume mass (d)			1.27 ± 0.04	g/cm³	TS 3078
Water absorption rate b	y mass (s)	18 m	Maximum1.5	%	TS 3078
	Tensile strenght	σ_1	Maximum0.80 x σ ₀	N/mm²	TS 3078
		Rate of change	Maximum 20	%	TS 3078
	Elongation rate at break	ε_1	At least 0.80 x ε_0	%	TS 3078
After aging		Rate of change	Maximum 20	%	TS 3078
	Type A Shore durometer hardness rating	H ₁	$H_o \pm 5$	Shore A	TS 3078
		Amount of change	± 5	Shore A	TS 3078
Residue fraction by mas	s (k)		Maximum 5.0 (m/m)	%	TS 3078

ARFEN İNŞAAT VE YAPI TEKNOLOJİLERİ SAN. TİC. A.Ş.

Arfen Headquarter: İstanbul / Türkiye T: +90 212 485 16 15 arfen@arfen.com