

DA 32-4 TYPE WATERSTOP

(Expansion Joint Waterstop Placed Outside Concrete)

- A waterstop placed on the outer surface of a concrete structural element with a flat outer surface, an expansion gap in the center and parallel profiles on both sides of the gasket sections perpendicular to the longitudinal axis of the gasket to prevent the gasket from peeling out of the concrete.
- Resistant to high water pressures.
- Waterstop tapes can be joined to each other by heat (thermal) welding (150 °C - 180 °C).



TECHNICAL DATA


General Application Areas of Waterstop

- ➤ Dams,
- Irrigation canals,
- Water tanks, reservoirs,
- Water purification plants,
- Swimming pools,
- Docks Transmission tunnels,
- Hydroelectric power plants,
- > Bridges,
- Metro constructions,
- Viaducts,
- Retaining walls,
- Slabs on ground and foundations,
- Industrial structures.
- Production length 20 meters.

ARFEN İNŞAAT VE YAPI TEKNOLOJİLERİ SAN. TİC. A.Ş.

Arfen Headquarter: İstanbul / Türkiye T: +90 212 485 16 15 arfen@arfen.com





h

i

L

m

Ν

s

- Total width а Width of the expansion section b
- Thickness at the thinnest part of the expansion section С
- Distance between axes of notched anchor threads е
- f Height of notched anchor thread

g

- Height of notched anchor thread (excluding thickness) f₁
- Notched anchor thread head thickness

Thickness at the thinnest part of the notched anchor thread

- k Expansion gap width
 - Expansion gap height
 - Wall thickness at the thinnest part of the expansion gap
 - Number of notched anchor threads
 - Width of anchor section (e x (N-1))

Thickness of notched anchor thread at the joint Type DA waterstop cross-section

Type DA waterstop nominal dimensions (mm)

Product	a	b	c	N	e	f	f₁	g	h	i	k	l	m
Code	Min.	Min.	Min.	Min.	Min.	Min.	Min.	Min.	Min.	Min.	Min.	Min.	Min.
DA 32-4	320	100	4	6	45	25	21	4 ≥ c ≥ 0.2f	4	11 ≥ h+6	20	20	4

Tolerances for length dimensions

Nominal Size Range (mm)											
< 3	≥3 <6	≥6 <10	≥ 10 < 18	≥ 18 < 30	≥ 30 < 50	≥ 50 < 80	≥ 80 < 120	≥ 120 < 180	≥ 180 < 250	≥ 250 < 320	≥ 320
± 0.3	± 0.4	± 0.5	± 0.6	± 0.7	± 0.8	± 1.0	± 1.2	± 1.4	± 1.7	± 2.0	± %0.8

Tolerances for wall thicknesses

Nominal Size Range (mm)							
< 1.2	≥ 1.2 < 2.5	≥ 2.5 < 4	≥4 <6.5	≥ 6.5 < 10	≥ 10		
± 0.2	± 0.3	± 0.4	± 0.5	± 0.6	± %0.8		



Mechanical Properties

Analysis	Standard	Basic requirement
Appearance inspection	TS 3078-2	No gaps, cracks, shrinkage, etc.
Size inspection	TS 3078-2	Dimensions must comply with TS 3078-1
Shore A hardness	TS 3078-2	70 ± 5
Tensile strength	TS 3078-2	≥ 10 MPa
Elongation rate at break	TS 3078-2	≥ %275
Tear resistance	TS 3078-2	≥ 12 kN/m
Low temperature behavior: Elongation at break at-20 °C	TS 3078-2	≥ %200
 Behavior: a) After soaking in slaked lime milk b) Behavior in the face of heat c) Behavior after aging Percentage change in the average value compared to the initial value: 	TS 3078-2	
Tensile strength Elongation rate at break Modulus of elasticity		≤ %20 ≤ %20 ≤ %50
Joint strength Short-term junction factor (f_z)	TS 3078-2	Rupture outside the weld zone or ≥ 0.6
Fire reaction class according to TS EN 13501-1+A1	TS 3078-2	Class E must be
Residue fraction by mass	TS 3078-2	< %5.0

ARFEN İNŞAAT VE YAPI TEKNOLOJİLERİ SAN. TİC. A.Ş.

Arfen Merkez: İstanbul / Türkiye T: +90 212 485 16 15 arfen@arfen.com