

I 32-6 TYPE WATERSTOP


- ➤ It is used at the joints of raft foundation raft foundation, raft foundation shear wall or shear wall shear wall in structures exposed to low and high water pressure in full and partial contraction joints.
- ➤ Waterstops can be joined to each other by heat (thermal) welding (150 °C 180 °C).



TECHNICAL DATA

General Application Areas of Waterstop

- > Dams,
- > Irrigation canals,
- Water tanks, reservoirs,
- Water purification plants,
- Swimming pools,
- Docks Transmission tunnels,
- Hydroelectric power plants,
- Bridges,
- Metro constructions,
- Viaducts,
- Retaining walls,
- Slabs on ground and foundations,
- Industrial structures.



Product Code	L	a ₁	b	Set Quantity	с	d	e	f	g	h	k	Production Length
132-6	320 ± 5	6 ± 0.5	26	8	21 ± 2	4	8	4± 0.5	16± 1	3	14± 2	20 meters

Waterstop dimensions are in millimeters.

www.arfen.com - www.arfen.eu - www.arfenusa.com



Mechanical Properties

Analysis		Basic requireme	nt	Unit	Standard
Tensile strenght (σ_0)	Ave	rage value	At least 14	N/mm²	TS 3078
Tensile strengitt (0 ₀)	Sma	llest value	At least 12	N/mm²	TS 3078
Elongation rate at	Ave	rage value	At least 225	%	TS 3078
break (ε_0)	Sma	llest value	At least 200	%	TS 3078
Type A Shore durometer	r hardness rating	(H _o)	75 ± 5	Shore A	TS 3078
Unit volume mass (d)			1.27 ± 0.04	g/cm³	TS 3078
Water absorption rate b	oy mass (s)	137	Maximum1.5	%	TS 3078
	Tensile	σ_1	Maximum0.80 x σ ₀	N/mm²	TS 3078
	strenght	Rate of change	Maximum 20	%	TS 3078
A.C	Elongation	$arepsilon_1$	At least 0.80 x ε_0	%	TS 3078
After aging	rate at break	Rate of change	Maximum 20	%	TS 3078
	Type A Shore durometer	H ₁	H _o ± 5	Shore A	TS 3078
	hardness rating	Amount of change	± 5	Shore A	TS 3078
Residue fraction by mas	s (k)		Maximum 5.0 (m/m)	%	TS 3078